# **3M** Window Films



## Ceramic Series CM 40

Scan for ratings and reviews



## Clear Energy Savings



### Ceramic Series benefits:

- Natural tone with amazing clarity
- High heat rejection provides energy savings and improves comfort
- Low reflectivity enhances views and overall beauty
- Significantly extends the life of furnishings by rejecting UV rays, the single largest cause of fading
- Non-metal technology eliminates corrosion
- Reduces glare and eye discomfort
- Increases personal safety by minimizing flying glass
- Comprehensive 3M manufacturers warranty

#### **Performance results\*:**

| Visible Light Transmitted    | 44%  |
|------------------------------|------|
| Total Solar Energy Rejected  | 53%  |
| Solar Heat Gain Coefficient  | 0.47 |
| Infrared Rejected            | 78%  |
| Solar Heat Reduction         | 43%  |
| Visible Light Reflected Int. | 12%  |
| Visible Light Reflected Ext. | 14%  |
| UV Rejected                  | 99%  |
| Glare Reduction              | 50%  |

\*Performance data generated for a typical film on 6mm glass using applicable industry test methods and standards. Infrared rejection measured from 900nm – 1000nm.

Interior View



Scan for ratings and reviews



**Clear Energy Savings** 



| Glass Type<br>(All 1/4")        | Single<br>Pane<br>Clear | Single<br>Pane<br>Tinted | Double<br>Pane<br>Clear | Double<br>Pane<br>Tinted |
|---------------------------------|-------------------------|--------------------------|-------------------------|--------------------------|
| Visible Light<br>Transmitted    | 44%                     | 27%                      | 40%                     | 24%                      |
| Total Solar<br>Energy Rejection | 53%                     | 59%                      | 46%                     | 60%                      |
| Solar Heat Gain<br>Coefficient  | 0.47                    | 0.41                     | 0.54                    | 0.40                     |
| Solar Heat<br>Reduction         | 43%                     | 34%                      | 23%                     | 21%                      |
| Visible Light<br>Reflected Int. | 12%                     | 11%                      | 14%                     | 13%                      |
| Visible Light<br>Reflected Ext. | 14%                     | 8%                       | 20%                     | 10%                      |
| UV Light Rejected               | 99%                     | 99%                      | 99%                     | 99%                      |
| Glare Reduction                 | 50%                     | 50%                      | 50%                     | 50%                      |
| Shading<br>Coefficient          | 0.54                    | 0.47                     | 0.62                    | 0.46                     |
| U Value                         | 1.03                    | 1.03                     | 0.47                    | 0.47                     |

\*Performance data generated for a typical film on 6mm glass using applicable industry test methods and standards. Infrared rejection measured from 900nm – 1000nm. This data represents center of glass values in accordance to NFRC 100/200, and is measured on NFRC required glass types, actual performance will vary with specific glass type.





**Renewable Energy Division** 

3M Center, Building 235-2S-27 St. Paul, MN 55144-1000 www.3m.com/windowfilm

© 3M 2011. 3M is a registered trademark of 3M Company. 70-0709-0363-1 (111.5)ii



Exterior View





